



سهامی خاص ثبت ۴۸۴۶۱

شرکت صنایع شیمیایی آذین بسپار سپاهان

(Pu Adhesive, Polyol, Saturated polyester)

تولید کننده انواع پلی ال ها، پلی استرهای اشباع، چسبهای پلی یورتان

تاریخ:

شماره:

پیوست:

One-component paste polyurethane sealant (mastic)

This product is a one-component polyurethane resin with a physical state of paste based on MDI and isoforon diisocyanate with dry air mechanism, which is used as a sealant and one-component polyurethane adhesive. Very high ductility, excellent shelf life and resistance to yellowing, excellent resistance to environmental conditions and chemical solvents, as well as high shelf life and also odorless and environmentally friendly solvent.

- Other properties of this product include excellent 0% volume boost, as well as a completely bubble-free surface with no pores.
- This product is only available in 20 kg and 220 kg vacuum bag weights with a shelf life of three to six months. White is always available and other colors are produced according to the customer's order
- This product has many applications in the construction and automotive industries, some of which are mentioned below
- Sealing of ceramic tile seams of concrete and gypsum seams, as well as aluminum and iron pvc doors and windows, as well as sealing of dishwasher sinks, gluing of wood-plastic and heating floors, as well as sealing inside elevators and making cargo containers. Becomes.

Add : Sejzy Industrial Zone, Isfahan, Iran

Tel : +983146412415-7

Fax: +983146412411

Web : www.apspolymer.com

Email : info@apspolymer.com

آدرس : شهرک صنعتی بزرگ شرق اصفهان (سجزی) خیابان چهارم

شرقی - نبش فرعی پنجم - پلاک ۱۳

تلفن : ۰۳۱-۴۶۴۱۲۴۱۵-۷

فکس : ۰۳۱-۴۶۴۱۲۴۱۱

آدرس وب سایت : www.apspolymer.com

پست الکترونیک : info@apspolymer.com



سهامی خاص ثبت ۴۸۴۶۱

شرکت صنایع شیمیایی آذین بسپار سپاهان

(Pu Adhesive, Polyol, Saturated polyester)

تولید کننده انواع پلی ال ها، پلی استرهای اشباع، چسبهای پلی یورتان

تاریخ:

شماره:

پیوست:

TECHNICAL PROPERTIES:

comp A	M19pv	s3012380	s38035.
type	2 comp A/B	comp1	comp1
hardness	65-75	shore A 45	shore A 35
iso(comp B)	shoreA pm-200	---	---
volume change	max 2%	0.	0
mixing (A/B)	7/1 - 8/1 e	moisture cure	moisture cure
initial drying(min)	70	180	45 min
final drying	24 hr	48hr	24hr
pot life (min)	30	40_50	15-20
viscosity (cp)	paste	paste	paste
density (kg/m3)	1550	1550	1750
shelf life (month)		6	6

Add : Sejzy Industrial Zone, Isfahan, Iran

Tel : +983146412415-7

Fax: +983146412411

Web : www.apspolymer.com

Email : info@apspolymer.com

آدرس : شهرک صنعتی بزرگ شرق اصفهان (سجزی) خیابان چهارم

شرقی - نبش فرعی پنجم - پلاک ۱۳

تلفن : ۰۳۱-۴۶۴۱۲۴۱۵-۷

فکس : ۰۳۱-۴۶۴۱۲۴۱۱

www.apspolymer.com : آدرس وب سایت

info@apspolymer.com : پست الکترونیک